

# We are IntechOpen, the world's leading publisher of Open Access books Built by scientists, for scientists

4,400

Open access books available

117,000

International authors and editors

130M

Downloads

Our authors are among the

154

Countries delivered to

TOP 1%

most cited scientists

12.2%

Contributors from top 500 universities



WEB OF SCIENCE™

Selection of our books indexed in the Book Citation Index  
in Web of Science™ Core Collection (BKCI)

Interested in publishing with us?  
Contact [book.department@intechopen.com](mailto:book.department@intechopen.com)

Numbers displayed above are based on latest data collected.  
For more information visit [www.intechopen.com](http://www.intechopen.com)



# Generalized BCS Equations: A Review and a Detailed Study of the Superconducting Features of $\text{Ba}_2\text{Sr}_2\text{CaCu}_2\text{O}_8$

*Gulshan Prakash Malik and Vijaya Shankar Varma*

## Abstract

High- $T_c$  superconductors (SCs) are most widely studied via the multiband approach (MBA) based on the work of Suhl et al. and the Nambu-Eliashberg-McMillan extension of the BCS theory. Complementing MBA and presented in a recent monograph is an approach based on the generalized BCS equations (GBCSEs), which too has been applied to a significant number of SCs. GBCSEs are obtained via a Bethe-Salpeter equation and the Matsubara technique. One of the key features of this approach is the characterization of a composite SC by Cooper pairs with different binding energies—each of which is identified with a gap ( $\Delta$ ) of the SC—depending on whether pairing is due to phonon exchanges with one, two, or more ion species. Another feature is the incorporation of chemical potential in the GBCSEs, which enables one to calculate the critical current density  $j_0$  of an SC using the same parameters that determine its  $T_c$  and  $\Delta$ . Following a review of the concepts of this approach, given herein, for the first time, is a detailed explanation of the multitude of reported empirical values of  $\{T_c, \Delta, j_0\}$  of  $\text{Bi}_2\text{Sr}_2\text{CaCu}_2\text{O}_8$ . Also discussed are the currently topical issues of  $s^\pm$ -superconductivity and the isotope-like effect for high- $T_c$  SCs.

**Keywords:** high- $T_c$  superconductors, multiband approach, GBCSE-based approach, superconducting features of  $\text{Bi}_2\text{Sr}_2\text{CaCu}_2\text{O}_8$ ,  $s^\pm$ -superconductivity, isotope-like effect for high- $T_c$  superconductors, suggestions for further increasing the  $T_c$  of the Bi-based superconductors

## 1. Introduction

### 1.1 A historical note

The phenomenon of superconductivity was first observed by Kamerlingh Onnes [1] in 1911 while studying the electrical resistivity of metallic mercury as a function of temperature when cooled to liquid helium temperatures. He noticed that at the critical temperature  $T_c = 4.2 \text{ K}$  ( $-269^\circ\text{C}$ ), the resistance vanished abruptly. This was an exciting discovery because it suggested that such materials could have immense practical applications. Since cooling a material to very low temperatures is a tedious and expensive process, Onne's discovery triggered a

search in scientific laboratories across the world for other superconducting materials having  $T_c$ s higher than that of Hg, the ultimate aim being to find a material which is superconducting at room temperature. While this search led to the discovery of many elements and alloys that are superconductors (SCs), till as late as in the 1980s, the highest  $T_c$  of any known SC was about 23 K (for  $\text{Nb}_3\text{Sn}$ ). A radical change occurred in this situation in 1986 when Bednorz and Müller announced the discovery of an SC (Ba-La-Cu-O system) with  $T_c \approx 38$  K, for which they were awarded the Nobel Prize in 1987. An avalanche of activity followed soon thereafter leading to the discovery of many “high-temperature SCs” such as  $\text{MgB}_2$  ( $T_c \approx 40$  K), Fe-based SCs (highest  $T_c \approx 55$  K), and “cuprates,” examples of which are Bi-, Tl-, and Hg-based SCs that contain one or more units of  $\text{CuO}_2$  as a constituent, the  $T_c$ s of these SCs at ambient pressure being about 95, 110, and 138 K, respectively, and for the Hg-based SCs, going up to 164 K at high pressure. The confirmed current record for the highest  $T_c$  (203 K; at a pressure of 150 GPa) is held by  $\text{H}_3\text{S}$  which was discovered in 2015. It would thus appear that realization of the dream of room temperature SCs is near at hand.

On the theoretical front, a clear explanation of superconductivity evaded the efforts of many theoreticians who had been engaged in the quest. It was not until 46 years had elapsed since Onnes’ discovery that John Bardeen, Leon Cooper, and Robert Schrieffer (BCS) [2] were able to provide a generally accepted explanation of it for elemental SCs, for which they were awarded the Nobel Prize in 1972. Indeed, a contributing factor for this lag between theory and experiment was the tragedy of the two world wars in the intervening period.

BCS theory explains superconductivity as due to the formation of Cooper pairs (CPs), each of which is a bound state of two electrons. A well-known explanation for the origin of the attractive interaction causing electrons to be bound together is as follows: the passage of an electron through the ion lattice of an element leaves behind a deformation trail of enhanced positive charges. If a second electron passes through the lattice while it is recovering from the effect of the passage of the first, it will experience an attractive force that may be greater than the Coulomb repulsion between them. Hence, overall, the electron-lattice-electron interaction can be a net *weak* attractive interaction that leads to the formation of CPs. Since the bound state of two particles has lower energy than the state in which they are both free, the former becomes the preferred state leading to the occurrence of superconductivity. In the language of quantum field theory, it is said that the pairing of electrons takes place because they exchange a phonon due to the effect of the ion lattice. BCS theory is hence a weak-coupling theory which works for elemental SCs because the highest  $T_c$  for this class of SCs is about 9 K (for Nb). A general perception about this theory is that it is inadequate to explain the occurrence of such high- $T_c$ s as have been observed. This is indeed so if the one-phonon exchange mechanism (1PEM) is considered to be the sole mechanism responsible for pairing. Such a view overlooks the fact that *all* high- $T_c$  SCs are composite materials consisting of sub-lattices of more than one ion species and therefore the theory ought to be generalized to address the situation where CPs may also be formed due to more than 1PEM. Interestingly, as noted below, such a generalization can be carried out based on three theoretical developments that took place in the same decade, 1950s, to which the BCS theory belongs.

## 1.2 GBCSEs and their conceptual basis

Two of the three developments alluded to the above are widely known: the invention of the Bethe-Salpeter equation (BSE) in 1951 [3] and, in analogy with quantum field theory, the creation of a finite-temperature field theory (FTFT) by

Matsubara [4] in 1955. Not so well-known is the third development that took place in 1954 due to Okubo [5], viz., the introduction of the concept of a superpropagator as the propagator for the non-polynomial field  $\exp(g\phi)$  where  $g$  is a coupling constant and  $\phi$  a scalar field.

BSE is a four-dimensional equation which was invented for the description of bound states of two relativistic particles, hordes of which were being discovered in the late 1940s and early 1950s in cosmic rays and high-energy accelerators around the world. A general perception about the BSE is that it is irrelevant for superconductivity which is a strictly nonrelativistic phenomenon.

FTFT is obtained via an adaption of quantum field theory where time is replaced by temperature as the variable in terms of which evolution of a system is studied. Because temperature is a statistical concept, this is a huge step which converts an equation setup for the bound states of two particles interacting in vacuum into an equation valid in a many-body system. A shortcut known as the Matsubara prescription or recipe for introducing temperature into a BSE is to replace in it the component  $q_4$  of the four-vector  $q_\mu = (q_4, \mathbf{q})$  as follows (e.g., [6]):

$$\begin{aligned} q_4 &= (2n + 1)\pi/(-i\beta) \quad \text{for fermions} \\ &= 2n\pi/(-i\beta) \quad \text{for bosons} \end{aligned} \quad (1)$$

$$\int dq_4 = \frac{2\pi}{-i\beta} \sum_{n=-\infty}^{\infty}$$

Okubo's work remained an obscure academic exercise till Salam and collaborators found that non-polynomial theories have inbuilt damping effects. It was therefore hoped that they might provide the means of renormalizing, e.g., the weak interactions. These theories were not pursued any further after the gauge theory of interactions became widely accepted as the correct theory. However, it is relevant in the context of superconductivity to note that the expression for the Feynman superpropagator corresponding to the non-polynomial interaction  $1/(1 + g\phi)$  is [7]:

$$\Delta_F^{\text{SP}}(k) \approx \frac{1}{k^2 g^2} - \int_0^\infty dt \frac{e^{-t}(2-t)}{k^2 g^2 + t}. \quad (2)$$

The comparison of the above with the expression for one-particle Feynman propagator, viz.,

$$\Delta_F^{\text{1-Particle}}(k) = \frac{1}{k^2 - i\varepsilon} \quad (3)$$

reveals that a superpropagator represents a weighted superposition of multiple quanta. The significance of this remark emerges if we recall how the electron-lattice-electron interaction in an elemental SC causes formation of CPs via 1PEM. Appealing to the same picture for a composite SC, it follows that pairing can now also be caused via more than 1PEM because sub-lattices of ions of different masses are affected differently by the passage of electrons through the lattice of the SC. We are hence led to the following outline of a novel strategy for dealing with multicomponent SCs: start with a BSE for the bound states of two fermions, temperature-generalize it via the Matsubara prescription, and, for the kernel of the equation, employ a superpropagator representing exchange of multiple phonons for pairing.

To implement the above program, we need to employ (i) the instantaneous and mean-field approximations (IA, MFA), (ii) a model for fixing the Debye

temperatures of all the ions that may cause pairing, and (iii) the Bogoliubov constraint on the interaction parameters obtained via solutions of the equations that the BSE leads to when multi-phonon exchange mechanisms are operative. An account of these concepts is as follows.

By IA is meant that we ignore the time of propagation of the quanta, the exchange of which causes the electrons to be bound together. For example, in the momentum-space transform of the one-particle propagator in Eq. (3) where  $k^2 = k_0^2 - \mathbf{k}^2$ ,  $k_0^2$  is equated to zero. This is an essential step for the application of the Matsubara prescription which introduces temperature into the theory and reduces the BSE to a three-dimensional equation which is then subjected to the nonrelativistic approximation appropriate for superconductivity.

Employing MFA in the 1PEM scenario, one approximates the propagator noted in Eq. (3) by a constant,  $-V$  (as in  $[N(0)V]$ ,  $\hbar = c = 1$ ), because pairing takes place in a very small region demarcated by  $(E_F - k\theta \leq p^2/2m \leq E_F + k\theta)$ , where  $E_F$  denotes the Fermi energy,  $p^2/2m$  the energy of an electron, and  $\theta$  the Debye temperature of the SC; outside of this region,  $V = 0$ . Similarly, in the nPEM scenario, in lieu of the expression for the superpropagator in Eq. (2), one employs the expression  $-[V_1 + V_2 + \dots + V_n]$ , where  $n$  is the number of ion species that cause the electrons to form a pair,  $V_i$  corresponds to the phonon exchanged due to the  $i^{\text{th}}$  species of ions of which the Debye temperature is  $\theta_i$ , and  $(E_F - k\theta_i \leq p^2/2m \leq E_F + k\theta_i)$  is the region of pairing due to these ions, outside of which  $V_i = 0$ .

Given the Debye temperature  $\theta$  of any composite SC, we now need to fix the Debye temperatures of its constituent ion species,  $\theta_1, \theta_2$ , etc., which in general *must* be different from  $\theta$  because, as was first pointed out by Born and Karman a long time ago, elastic waves in an anisotropic material travel with different velocities in different directions; for a detailed account of their work, see [8]. We now draw attention to the fact that sublattices of all the high- $T_c$  SCs are composed of layers that contain either one or predominantly two ion species. The assumption that  $\theta$  is also the Debye temperature of each of these sub-lattices then fixes the Debye temperature of the sub-lattice of layers that contains a single ion species as  $\theta$ . As concerns fixing  $\theta_1$  and  $\theta_2$  for the sub-lattice comprising two ion species, we note that the following relation has been frequently used for finding the Debye temperature  $\theta$  of a binary  $A_xB_{1-x}$  when the Debye temperatures  $\theta_A$  and  $\theta_B$  are known:

$$\theta = x\theta_A + (1 - x)\theta_B. \quad (4)$$

Since we are faced with the inverse of the above situation, i.e., given  $\theta$ , we have to fix  $\theta_A$  and  $\theta_B$ , we now need to supplement Eq. (4) by another equation. We meet this requirement by assuming that the modes of vibration of the A and B ions simulate the weakly coupled modes of vibration of a double pendulum. This is suggested by the polariton effect where coupling between the phonon and the photon modes leads to two new modes, different from the original modes of either of them. With A as the upper bob in the double pendulum, we have our second equation as [10].

$$\frac{\theta_A}{\theta_B} = \left[ \frac{1 + \sqrt{m_B/(m_A + m_B)}}{1 - \sqrt{m_B/(m_A + m_B)}} \right]^{1/2}, \quad (5)$$

where  $m_A$  and  $m_B$  are the atomic masses of the ions.

Given  $\theta$  ( $\text{Bi}_2\text{Sr}_2\text{CaCu}_2\text{O}_8$ ) = 237 K,  $m_{\text{Bi}} = 208.98$ ,  $m_{\text{Sr}} = 87.62$ , and  $m_{\text{O}} = 15.999$  (amu), the application of Eqs. (4) and (5) leads to

$$\theta_{Ca} = 237 \text{ K}, \theta_{Bi} = 269 \text{ K}, \theta_{Sr} = 286 \text{ K}. \quad (6)$$

We note that (i)  $\theta_{Ca}$  equals the Debye temperature of the SC because the layers containing Ca ions do not have any other constituent. (ii) The value of  $\theta_{Bi}$  corresponds to Bi being the upper bob of the double pendulum and O the lower bob in the BiO layers; the other value of  $\theta_B$  when Bi is the lower bob is 57 K. (iii) The value of  $\theta_{Sr}$  also corresponds to Sr. being the upper bob of the double pendulum in the SrO layers; the other value of  $\theta_{Sr}$  is 81 K. (iv) The values of  $\theta_O$  in the two layers are not noted because they do not play a direct role in the pairing process. (v) Since we have four distinct choices for values of the pair  $\{\theta_{Bi}, \theta_{Sr}\}$ , we need a criterion for choosing one among them, and this is provided by the Bogoliubov constraint discussed below.

In a rigorous study concerned with renormalization of the BCS theory, starting with the assumption of a net attractive interaction between electrons, Bogoliubov found that the interaction parameter  $\lambda$  governing the pairing process must not exceed 0.5, otherwise the system would be unstable; for a detailed discussion, see [9]. Imposition of this constraint on the  $\lambda$ s obtained via GBCSEs for high- $T_c$  SCs is crucial. This is so because if one calculates  $\lambda$ s for each of the four choices of  $\theta$ s as noted above, one can straightway reject those that lead to any of them that are negative and choose among the rest the ones that lead to values closest to 0.5. The values of  $\theta$ s in Eq. (6) have been chosen on this basis.

### 1.3 Plan of the chapter

This chapter is organized as follows. In Section 2.1 is given the parent Bethe-Salpeter equation from which GBCSEs for the  $T_c$  and  $\Delta$ s of a multicomponent SC are derived. In Section 2.2, after an outline of the key steps of their derivation, are given the GBCSEs which are constrained by the inequality  $E_F \gg k\theta$ . More generally,  $E_F$ -incorporated GBCSEs, which are not constrained by this inequality, are given in Section 2.3. This is followed up by an account of similar equations, i.e., subject to and not subject to the said inequality, for the dimensionless construct  $y = (k\theta/P_0)\sqrt{2m/E_F}$ , which is required for calculating  $j_0$  and several other parameters of an SC. In Section 4 are listed the properties of Bi-2212, the explanation of which is taken up in Section 5. In Section 6 we draw attention to the application of the framework of GBCSEs to a diverse variety of SCs, viz., LCO, the heavy fermion, and the Fe-based SCs. Also included in this section is a brief account of a recent study concerned with the isotope-like effect for Bi-2212. Sections 6 and 7 are devoted, respectively, to the discussion of the key features of our approach and the conclusions following from them.

## 2. The framework of GBCSEs

After an outline of the key steps of their derivation, we give in this section the GBCSEs that are later employed for the study of various superconducting features of  $\text{Bi}_2\text{Sr}_2\text{CaCu}_2\text{O}_8$  (Bi-2212). We refer the reader to [10] for a detailed derivation of these equations.

### 2.1 The parent BSE

The parent equation from which GBCSEs are derived is the following relativistic BSE [11] for the bound states of fermions 1 and 2 of equal mass ( $m$ ):

$$\begin{aligned} \psi(p_\mu) = & (-2\pi i)^{-1} \int d^4 q_\mu \frac{1}{\gamma_\mu^{(1)} P_\mu / 2 + \gamma_\mu^{(1)} q_\mu - m + i\epsilon} \\ & \times \frac{1}{\gamma_\mu^{(2)} P_\mu / 2 + \gamma_\mu^{(2)} q_\mu - m + i\epsilon} I(q_\mu - p_\mu) \psi(q_\mu), \end{aligned} \quad (7)$$

where  $\psi$  is the BS amplitude for the formation of the bound state of the two particles,  $P_\mu$  the total four-momentum of their center of mass,  $q_\mu$  their relative four-momentum,  $\gamma_\mu^{(1,2)}$  are their Dirac matrices, and  $I(q_\mu - p_\mu)$  is the kernel of the equation that causes the particles to be bound together; the metric employed is time-preferred:  $a_\mu b_\mu = a_4 b_4 - \mathbf{a} \cdot \mathbf{b}$ .

## 2.2 GBCSEs corresponding to multiphonon exchanges for pairing

We now outline how GBCSEs are derived when CPs in an SC are formed due to multi-phonon exchange mechanisms subject to the following constraint:

$$E_F \gg k\theta, \quad (8)$$

where  $\theta$  is the Debye temperature of the SC.  
Beginning with Eq. (7), we obtain GBCSEs by:

1. Employing IA:  $I(q_\mu - p_\mu) = I(\mathbf{q} - \mathbf{p})$
2. Carrying out spin reduction of the equation by multiplying it with Dirac matrices  $\gamma_4^{(1)} \gamma_4^{(2)}$
3. Working in the rest frame of the two particles:  $P_\mu = (E, 0)$
4. Putting  $E = 2E_F + W$
5. Temperature-generalizing the equation via the Matsubara recipe given in the previous section
6. Assuming that the signature of  $W$  changes on crossing the Fermi surface
7. Choosing for the kernel a generalized form of the model BCS interaction:

$$\begin{aligned} I(\mathbf{q} - \mathbf{p}) = & \sum_{i=1}^n \frac{-V_i}{(2\pi)^3} \left( \text{for } E_F - k\theta_i \leq \frac{\mathbf{p}^2}{2m}, \frac{\mathbf{q}^2}{2m} \leq E_F + k\theta_i \right) \\ = & 0 \text{ (otherwise),} \end{aligned} \quad (9)$$

where  $n$  is the number of ion species due to which pairs are formed and  $\theta_i$  is the Debye temperature of the  $i^{\text{th}}$  species of ions

8. Calculating  $\theta_i$  via the Debye temperature  $\theta$  of the SC and Eqs. (4) and (5) given above

With their application to Bi-2212 in mind, given below are the equations that the above steps lead to in the scenario in which the smaller of the two gaps of an SC is due to a two-phonon exchange mechanism (2PEM) and its larger gap and the

highest  $T_c$  are due to a three-phonon exchange mechanism (3PEM) (reminder:  $E_F \gg k\theta$ )

$$1 = \lambda_1 \ln \left[ 1 + \frac{2k\theta_1}{|W_2|} \right] + \lambda_2 \ln \left[ 1 + \frac{2k\theta_2}{|W_2|} \right] \quad (10)$$

$$1 = \lambda_1 \ln \left[ 1 + \frac{2k\theta_1}{|W_3|} \right] + \lambda_2 \ln \left[ 1 + \frac{2k\theta_2}{|W_3|} \right] + \lambda_3 \ln \left[ 1 + \frac{2k\theta_3}{|W_3|} \right] \quad (11)$$

$$1 = \lambda_1 \int_0^{\theta_1/2kT_c} dx \frac{\tanh(x)}{x} + \lambda_2 \int_0^{\theta_2/2kT_c} dx \frac{\tanh(x)}{x} + \lambda_3 \int_0^{\theta_3/2kT_c} dx \frac{\tanh(x)}{x}, \quad (12)$$

where  $\lambda_i = [N(0)V_i]$ ,  $N(0) = (2m)^{3/2}E_F^{1/2}/4\pi^2$  ( $\hbar = c = 1$ ).

Remark: If  $\lambda_2 = 0$  in Eq. (10) and  $\lambda_2 = \lambda_3 = 0$  in both Eqs. (11) and (12), then we have a one-phonon exchange mechanism (1PEM) in operation. In this case Eq. (12) becomes identical with the BCS equation for the  $T_c$  of an elemental SC, whereas Eq. (10), or Eq. (11), leads to

$$|W_1| = 2k\theta / [\exp(1/\lambda) - 1].$$

Recalling the BCS equation for the gap of an elemental SC at  $T = 0$ , i.e.,

$$\Delta_0 = k\theta / \sinh(1/\lambda),$$

we observe that  $|W_1| = \Delta_0 = 2k\theta \exp(-1/\lambda)$ , when  $\lambda \rightarrow 0$ . This per se suggests that one may employ the equation for  $|W_1|$  in lieu of the equation for  $\Delta_0$ . Based on the values of  $|W_1|$  and  $\Delta_0$  obtained via a detailed study of six elemental SCs [10] by employing the empirical values of their Debye temperatures, it has been shown that  $|W_1|$  is a viable alternative to  $\Delta_0$ . We are thus led to assume that each of the three  $W$ s following from Eq. (11) is to be identified with a gap of the SC and that  $|W_3| > |W_2| > |W_1|$ , where  $|W_2|$  corresponds to the solution of the equation when one of the  $\lambda$ s is zero and  $|W_1|$  to when two of them are zero.

### 2.3 $E_F$ -incorporated GBCSEs

It has been known for a long time that  $T_c$ s of some SCs—SrTiO<sub>3</sub> being a prime example—depend in a marked manner on their electron concentration  $n_s$  which is related to  $E_F$ . Recent studies—both experimental [12–14] and theoretical [15–17]—too suggest that *low* values of  $E_F$  play a fundamental role in determining the properties of high- $T_c$  SCs. This makes it natural to seek equations for the  $T_c$ s and  $\Delta$ s of these SCs that incorporate  $E_F$  as a variable and are therefore not constrained by inequality (8). Such equations are in fact an integral part of the BCS theory. Their application to dilute SrTiO<sub>3</sub> by Eagles [18] perhaps marks the beginning of what is now known as BCS-BEC crossover physics. It seems to us that the focus of crossover physics has, by and large, been different from that of the studies of high- $T_c$  SCs.

Beginning with Eq. (7) and carrying out steps (1–8) noted above, without imposing inequality (8), the  $\mu$ -incorporated GBCSEs corresponding to Eqs. (10)–(12) are as follows [10]:

$$\frac{\lambda_1}{2} a_1(\mu_0) + \frac{\lambda_2}{2} a_2(\mu_0) = \left[ \frac{3}{4} a_3(\mu_0) \right]^{1/3} \quad (13)$$

$$\frac{\lambda_1}{2} b_1(\mu_0) + \frac{\lambda_2}{2} b_2(\mu_0) + \frac{\lambda_3}{2} b_3(\mu_0) = \left[ \frac{3}{4} b_4(\mu_0) \right]^{1/3} \quad (14)$$



$$\frac{\lambda_1}{2}c_1(\mu_1) + \frac{\lambda_2}{2}c_2(\mu_1) + \frac{\lambda_3}{2}c_3(\mu_1) = \left[\frac{3}{4}c_4(\mu_1)\right]^{1/3}, \quad (15)$$

where  $\mu_0$  ( $\mu_1$ ) is the chemical potential at  $T = 0$  ( $T = T_c$ ) and  $\mu_0$  has been used interchangeably with  $E_F$ ,

$$a_1(\mu_0) = \mathbf{Re} \left[ \int_{-k\theta_1}^{k\theta_1} d\xi \frac{\sqrt{\xi + \mu_0}}{|\xi| + |W_2|/2} \right], a_2(\mu_0) = \mathbf{Re} \left[ \int_{-k\theta_2}^{k\theta_2} d\xi \frac{\sqrt{\xi + \mu_0}}{|\xi| + |W_2|/2} \right]$$

$$a_3(\mu_0) = \mathbf{Re} \left[ \frac{4}{3}(\mu_0 - k\theta_m)^{3/2} + \int_{-k\theta_m}^{k\theta_m} d\xi \sqrt{\xi + \mu_0} \left(1 - \frac{\xi}{\sqrt{\xi^2 + W_2^2}}\right) \right]$$

$$b_1(\mu_0) = \mathbf{Re} \left[ \int_{-k\theta_1}^{k\theta_1} d\xi \frac{\sqrt{\xi + \mu_0}}{|\xi| + |W_3|/2} \right], b_2(\mu_0) = \mathbf{Re} \left[ \int_{-k\theta_2}^{k\theta_2} d\xi \frac{\sqrt{\xi + \mu_0}}{|\xi| + |W_3|/2} \right]$$

$$b_3(\mu_0) = \mathbf{Re} \left[ \int_{-k\theta_3}^{k\theta_3} d\xi \frac{\sqrt{\xi + \mu_0}}{|\xi| + |W_3|/2} \right]$$

$$b_4(\mu_0) = \mathbf{Re} \left[ \frac{4}{3}(\mu_0 - k\theta_2)^{3/2} + \int_{-k\theta_m}^{k\theta_m} d\xi \sqrt{\xi + \mu_0} \left(1 - \frac{\xi}{\sqrt{\xi^2 + W_3^2}}\right) \right]$$

$$c_1(\mu_1) = \mathbf{Re} \left[ \int_{-\theta_1/2T_{c3}}^{\theta_1/2T_{c3}} dx \sqrt{2kT_{c3}x + \mu_1} \frac{\tanh(x)}{x} \right],$$

$$c_2(\mu_1) = \mathbf{Re} \left[ \int_{-\theta_2/2T_{c3}}^{\theta_2/2T_{c3}} dx \sqrt{2kT_{c3}x + \mu_1} \frac{\tanh(x)}{x} \right]$$

$$c_3(\mu_1) = \mathbf{Re} \left[ \int_{-\theta_3/2T_{c3}}^{\theta_3/2T_{c3}} dx \sqrt{2kT_{c3}x + \mu_1} \frac{\tanh(x)}{x} \right]$$

$$c_4(\mu_1) = \mathbf{Re} \left[ 2kT_{c3} \int_{-\theta_m/2T_{c3}}^{\theta_m/2T_{c3}} dx \sqrt{2kT_{c3}x + \mu_1} \{1 - \tanh(x)\} \right],$$

$\theta_m$  is the Debye temperature that has the highest value among all the Debye temperatures being used (when  $\lambda_2 \neq 0$ ,  $\theta_m = \theta_2$ ; when  $\lambda_2 = 0$ ,  $\theta_m = \theta_3$ ; when  $\lambda_2 = \lambda_3 = 0$ ,  $\theta_m = \theta_1$ ), and the operator  $\mathbf{Re}$  ensures that the integrals yield real values even when expressions under the radical signs are negative.

#### 2.4 Equation for $y = (k\theta/P_0)\sqrt{2m/E_F}$ ( $E_F \gg k\theta$ )

If it turns out that we need to employ the  $\mu$ -incorporated Eqs. (13)–(15) to deal with high- $T_c$  SCs, rather than Eqs. (10)–(12), as will be shown to be the case, then there will be a need for at least one more equation for an additional property of the SC, besides equations for one of its  $T_c$  and  $\Delta_s$ , in order to fix the values of  $\mu_s$  and  $\lambda_s$  that lead to various empirical features of the SC. We choose the critical current density  $j_0$  of the SC at  $T = 0$  to meet this need.

The BSE-based approach enables one to derive an equation for  $j_0$  of an SC by employing the same values of  $\theta_s$  and  $\lambda_s$  that determine a given value of its  $T_c$  and different values of its  $\Delta_s$ . This comes about because one can now obtain expressions for the effective mass  $m^*$  of an electron, critical velocity  $v_0$  at  $T = 0$ , and the number of

superconducting electrons  $n_s$  at  $T = 0$ , and hence for  $j_0$  in terms of  $y$  and the values of the following other parameters of the SC:  $\theta$ , the electronic specific heat constant  $\gamma, s \equiv m^*/m_e, v_0, n_s$ , and  $v_g$ , where  $m_e$  is the free electron mass and  $v_g$  the gram-atomic volume of the SC.

As concerns  $y$ , we recall that in the original BCS theory, the Hamiltonian was restricted at the outset to comprise terms corresponding to pairs having zero center-of-mass momentum. The BSE-based approach enables one to go beyond this restriction by setting  $P_\mu = (E, \mathbf{P})$ , rather than  $(E, 0)$ , where  $\mathbf{P}$  is the three-momentum of CPs in the lab frame. Beginning with Eq. (7) and carrying out essentially the same steps as for the  $P_\mu = (E, 0)$  case, we now obtain in the 3PEM scenario the following equation for  $y$  [10], which can be solved after the  $\lambda$ s have been determined by solving Eqs. (10)–(12):

$$1 = \lambda_1 t(r_1, y) + \lambda_2 t(r_2, y) + \lambda_3 t(r_3, y), \quad (16)$$

where

$$t(r, y) = \left[ r y \ln \left( \frac{r y}{r y - 1} \right) + \ln (r y - 1) \right], r_i = \theta_i / \theta.$$

Note that equating one (two) of the  $\lambda$ s in Eq. (16) to zero, we obtain the equation for  $y$  in the 2PEM (1PEM) scenario.

In terms of  $y$  and the other parameters mentioned above, it has been shown in [19, 20] that

$$s \equiv m^*/m_e = A_1 \frac{(\gamma/v_g)^{2/3}}{E_F^{1/3}} \quad (17)$$

$$n_s(E_F) = A_2 (\gamma/v_g) E_F \quad (18)$$

$$P_0(E_F) = A_3 \frac{\theta (\gamma/v_g)^{1/3}}{y E_F^{2/3}} \quad (19)$$

$$v_0(E_F) = A_4 \frac{\theta}{y (\gamma/v_g)^{1/3} E_F^{1/3}} \quad (20)$$

and hence

$$j_0(E_F) = \frac{n_s(E_F)}{2} e^* v_0(E_F) = A_5 \frac{\theta}{y} (\gamma/v_g)^{2/3} E_F^{2/3}, \quad (e^* = 2e) \quad (21)$$

where  $e$  is the electronic charge, and

$$A_1 \cong 3.305 \times 10^{-10} \text{ eV}^{-1/3} \text{ cm}^2 \text{ K}^{4/3},$$

$$A_2 \cong 2.729 \times 10^7 \text{ eV}^{-2} \text{ K}^2, A_3 \cong 1.584 \times 10^{-6} \text{ cm K}^{-1/3},$$

$$A_4 \cong 1.406 \times 10^8 \text{ eV}^{2/3} \text{ sec}^{-1} \text{ K}^{-5/3}, \text{ and } A_5 \cong 6.146 \times 10^{-4} \text{ CeV}^{-4/3} \text{ K}^{1/3} \text{ s}^{-1}.$$

## 2.5 $E_F$ -dependent equation for $y = (k\theta/P_0)\sqrt{2m/E_F}$

If the  $T_c$  and  $\Delta$ s of an SC are studied via Eqs. (10)–(12), which are valid when  $E_F \gg k\theta$ , then it is appropriate to employ Eq. (16) for  $y$  because it too is valid when the same inequality is satisfied. If it turns out that we need to employ the  $\mu$ -incorporated Eqs. (13)–(15) in lieu of Eqs. (10)–(12), then consistency demands that we employ for  $y$ , in lieu of Eq. (16), an equation that too is explicitly  $\mu$ -dependent.

The desired equation for  $y$  in the 3PEM scenario, obtained by setting  $P_\mu = (E, \mathbf{P})$  in the BSE and doing away with the earlier constraint on  $E_F$ , is [21]:

$$1 = \frac{\lambda_1}{4} T(\Sigma'_1, r_1 y) + \frac{\lambda_2}{4} T(\Sigma'_2, r_2 y) + \frac{\lambda_3}{4} T(\Sigma'_3, r_3 y), \quad (22)$$

where

$$\begin{aligned} T(\Sigma', y) &= \mathbf{Re} \left[ \int_0^1 dx F(\Sigma', x, y) \right], F(\Sigma', x, y) = f_1(\Sigma', x, y) + f_2(\Sigma', x, y) \\ f_1(\Sigma', x, y) &= 4 [-u_1(\Sigma', x, y) - u_2(\Sigma', x, y) + u_3(\Sigma', x, y) + u_4(\Sigma', x, y)], \\ f_2(\Sigma', x, y) &= 2 \ln \left[ \frac{1 + u_1(\Sigma', x, y)}{1 - u_1(\Sigma', x, y)} \frac{1 + u_2(\Sigma', x, y)}{1 - u_2(\Sigma', x, y)} \frac{1 - u_3(\Sigma', x, y)}{1 + u_3(\Sigma', x, y)} \frac{1 - u_4(\Sigma', x, y)}{1 + u_4(\Sigma', x, y)} \right] \\ u_1(\Sigma', x, y) &= \sqrt{1 - \Sigma' x / y}, u_2(\Sigma', x, y) = \sqrt{1 + \Sigma' x / y} \\ u_3(\Sigma', x, y) &= \sqrt{1 - \Sigma' (1 - x / y)}, u_4(\Sigma', x, y) = \sqrt{1 + \Sigma' (1 - x / y)} \\ \Sigma' &= k\theta / E_F, \Sigma'_i = k\theta_i / E_F, r_i = \theta_i / \theta. \end{aligned}$$

Equating one (two) of the  $\lambda$ s in Eq. (22) to zero, we obtain the  $\mu$ -dependent equation for  $y$  in the 2PEM (1PEM) scenario.

### 3. Superconducting features of $\text{Bi}_2\text{Sr}_2\text{CaCu}_2\text{O}_8$ addressed in this paper

The reported empirical values of  $\{T_c, \Delta\}$  of the above SC are [22], p 447:

$$\{T_c \text{ (K)}, \Delta \text{ (meV)}\} = \{95, 38\}, \{86, 28\}, \{62, 18\}. \quad (23)$$

As concerns empirical values of  $j_0$  of the SC, the situation is rather complicated because 14 values of this parameter have been reported in [22], p 468—depending upon the shape of the SC, how it is doped, and the values of temperature and the external magnetic field  $H$  under which they were determined. However, none of these values corresponds to the  $T = H = 0$  scenario employed by us. The value  $j_0 = 10^6 \text{ A/cm}^2$  at  $T = 4.4 \text{ K}$  and unspecified value of  $H$  being closest to it. Another value of interest for us is [23]:

$$j_0 = 3.2 \times 10^7 \text{ A/cm}^2 \text{ (} T = 4.2 \text{ K, } H = 12 \text{ Tesla)}. \quad (24)$$

In the following we give a quantitative explanation of the values of the parameters noted in Eqs. (23) and (24) and a plausible explanation of the multitude of the other values of these parameters.

## 4. An explanation of the multiple $\{T_c, \Delta, j_0\}$ -values of Bi-2212 via GBCSEs

### 4.1 Earlier work

In our earlier work dealing with the above SC [10], we had employed GBCSEs constrained by inequality (8) and had restricted ourselves to the 2PEM scenario. The maximum value of  $\Delta$  that we could then account for, subject to the Bogoliubov

constraint, was 20.4 meV corresponding to  $T_c = 95$  K. Subsequently, even after employing  $\mu$ -incorporated GBCSEs which are not constrained by inequality (8), we found that the 2PEM scenario was inadequate in explaining a value of  $\Delta$  exceeding 20.4 meV [20, 21]. What remained elusive in these studies were especially the value  $\Delta = 38$  meV and the other values of  $T_c$  and  $\Delta$  noted in Eq. (23). We show below how this lacuna is met via 3PEM in the present work.

#### 4.2 GBCSEs constrained by inequality $E_F \gg k\theta$ : premises and results

Since working in the 2PEM scenario, both with the  $\mu$ -independent and  $\mu$ -dependent GBCSEs, the maximum value of  $\Delta$  satisfying the Bogoliubov constraint was found to be 20.4 meV; we assume here that among the values noted in Eq. (23),

$$\Delta_2 = 18 \text{ meV}, \Delta_3 = 38 \text{ meV}, T_{c3} = 95 \text{ K}, \quad (25)$$

i.e., as our notation suggests, we attribute the first parameter above to 2PEM and the other two parameters to 3PEM. With  $\theta$ s as given in Eq. (6), the solutions of Eqs. (10–12) lead to  $\{\lambda_{Ca}, \lambda_{Sr}, \lambda_{Bi}\} = \{42.7, -37.6, 1.38\}$ . Since these values are in conflict with the Bogoliubov constraint, in the absence of any other handle, we now systematically fine-tune the input values of the two  $\Delta$ s and  $T_c$ . We thus find that  $\lambda$ s satisfying this constraint can be found only for values of  $\Delta$ s and  $T_{c3}$  that are substantially different from their empirical values in Eq. (23). An example, in order to obtain the set  $\{\lambda_{Ca}, \lambda_{Sr}, \lambda_{Bi}\} = \{0.4652, 0.2291, 0.4856\}$  which satisfies the required constraint, we have to choose input values as  $\Delta_2 = 14 \text{ meV}$ ,  $\Delta_3 = 33.5 \text{ meV}$ , and  $T_{c3} = 141$  K. This is an unacceptable state of affairs, suggesting the need to have a handle other than variation of the  $\Delta$ s- and  $T_c$ -values of the SC to satisfy the Bogoliubov constraint. We show below how the  $\mu$ -incorporated Eqs. (13)–(15), which are not constrained by inequality (8), meet this need.

#### 4.3 Interaction parameters obtained via $\mu$ -incorporated GBCSEs

Before attempting to find the three  $\lambda$ s satisfying the Bogoliubov constraint by employing Eqs. (13)–(15) for the same inputs as in Eqs. (6) and (25) and using  $\mu$  as a handle, as a consistency check of these equations, we solve them for a value of  $\mu_0 \gg k\theta$ , say,  $\mu_0 = 100 k\theta$ . For this value of  $\mu_0 = \mu_1$ , or any other greater value, we find that  $\lambda_{Ca} = 42.69$ ,  $\lambda_{Sr} = -37.59$ , and  $\lambda_{Bi} = 1.38$ , which are precisely the values we had obtained above via Eqs. (10)–(12) for the same inputs. This establishes that Eqs. (13)–(15) provide a reasonable generalization of Eqs. (10)–(12) and may therefore be used for any values of  $\mu_0$  and  $\mu_1$ . If we now solve Eqs. (13)–(15) with the same inputs as before, but with progressively lower values of  $\mu_0 = \mu_1$ , we find that there is a marginal *increase* in the value of each of the  $\lambda$ s; an example, for  $\mu_0 = \mu_1 = 5 k\theta$ ,  $\lambda_{Ca} = 42.90$ ,  $\lambda_{Sr} = -37.78$ ,  $\lambda_{Bi} = 1.39$ . This suggests that the assumption that  $\mu_0 = \mu_1$  may not be valid. To check this, we solve our equations again with  $\mu_0 = 5 k\theta$  and  $\mu_1 = 0.2 \mu_0$ , to find that  $\lambda_{Ca} = 16.46$ ,  $\lambda_{Sr} = -15.56$ , and  $\lambda_{Bi} = 0.1144$ . It is thus confirmed that in adopting a low value of  $\mu_0$ , with  $\mu_1$  a small fraction of it, we are proceeding in the right direction. Following this course, we obtain the desired set of  $\lambda$  values corresponding to the  $T_c$  and  $\Delta$  values in Eq. (25) as

$$\{\lambda_{Ca}, \lambda_{Sr}, \lambda_{Bi}\} = \{0.3123, 0.4993, 0.5000\}, \quad (26)$$

when

$$\mu_0 = 1.95 k\theta (39.82 \text{ meV}), \mu_1 = 0.105 \mu_0 (4.18 \text{ meV}). \quad (27)$$

#### 4.4 Calculation of $y$ via the $\mu$ -dependent Equation (22)

A consistency check of Eq. (22): While both the  $\mu$ -independent Eq. (16) and the  $\mu$ -dependent Eq. (22) for  $y$  require as input the values of  $\theta$ s and  $\lambda$ s, the latter equation requires the additional input of the value of  $E_F$  [i.e.,  $\mu_0$ , as noted below Eq. (15)] for its solution. We recall that Eq. (16) was derived by assuming that  $\mu_0 \gg k\theta$ . Therefore if Eq. (16) is solved for any given values of  $\theta$ s and the  $\lambda$ s, and Eq. (22) is solved with the same inputs together with a value of  $\mu_0$  which is much greater than  $k\theta$ , then the solutions of both the equations should yield the same value for  $y$ . To carry out this test in detail, we solve Eq. (22) for values of  $\theta$ s as in Eq. (6) and those of  $\lambda$ s as in Eq. (26) for the following seven cases:  $\lambda_2 = \lambda_3 = 0$ ,  $\lambda_3 = \lambda_1 = 0$ ,  $\lambda_1 = \lambda_2 = 0$ ,  $\lambda_1 = 0$ ,  $\lambda_2 = 0$ ,  $\lambda_3 = 0$ , and  $\lambda_1 \neq \lambda_2 \neq \lambda_3 \neq 0$ . With the same values of the  $\theta$ s and  $\lambda$ s and  $\mu_0 = 100 k\theta$ , solutions of Eq. (22) yield exactly the same results as were obtained via Eq. (16). Some of the values so-obtained are as follows: when  $\lambda_2 = \lambda_3 = 0$  (1PEM scenario),  $y = 9.458$ ; when  $\lambda_2 = 0$  (2PEM scenario),  $y = 1.661$ ; and when none of the  $\lambda$ s = 0 (3PEM scenario),  $y = 1.195$ . Having thus shown that Eq. (22) is a reasonable generalization of Eq. (16) for arbitrary values of  $\mu_0$ , we now solve it for  $\mu_0 (= E_F)$  as given in Eq. (27) and values of  $\{\lambda, \theta\}$  for each of the seven cases just noted. The results of these calculations are given in **Table 1**.

S. no.	$\lambda_1\lambda_2\lambda_3$	$\theta_1\theta_2\theta_3$ (K)	$ W $ (meV)	$T_c$ (K)	$y$	$v_0$ $\times 10^5$ ( $\text{cms}^{-1}$ )	$j_0$ $\times 10^7$ ( $\text{Acm}^{-2}$ )	Remark
1	0.3123 0 0	237 - -	1.70	8.5	9.688	1.41	0.9	1PEM (Ca)
2	0 0.4993 0	- 286 -	7.40	44.4	2.726	4.99	3.2	1PEM (Sr)
3	0 0 0.5000	- - 269	7.01	28.5	2.886	4.72	3.0	1PEM (Bi)
4	0 0.4993 0.5000	- 286 269	26.3	76.8	1.326	10.3	6.6	2PEM (Sr + Bi)
5	0.3123 0 0.5000	237 - 269	17.4	54.1	1.671	8.15	5.2	2PEM (Ca + Bi)
6	0.3123 0.4993 0	237 286 -	18.0	62.4	1.613	8.44	5.4	2PEM (Ca + Sr)
7	0.3123 0.4993 0.5000	237 286 269	38	95	1.199	11.4	7.3	3PEM (Ca + Sr. + Bi)

$|W|$  and  $T_c$  are obtained by solving Eqs. (14) and (15), respectively, with the input of  $\mu_0 = 1.95 k\theta$  ( $\theta = 237$  K),  $\mu_1 = 0.105 \mu_0$ , different combinations of  $\lambda$ -values as given in Eq. (26), and the corresponding  $\theta$ -values given in Eq. (6). For each set of  $\{\mu_0, \theta, \lambda\}$ ,  $y$  is obtained by solving Eq. (22). With  $E_F = \mu_0$ ,  $\gamma = (8/15) \times 10^{-3}$  J,  $v_g = 9.05 \text{ cm}^3/\text{g-at}$ , and  $s = m^*/m_e = 4.97$ , vide Eq. (17), and  $n_s = 4.0 \times 10^{20}/\text{cm}^3$ , vide Eq. (18).  $v_0$  and  $j_0$  corresponding to each value of  $y$  are obtained via Eqs. (20) and (21), respectively, with  $\theta = 237$  K.

**Table 1.**

Values of various superconducting parameters of  $\text{Bi}_2\text{Sr}_2\text{CaCu}_2\text{O}_8$  obtained via GBCSEs.

#### 4.5 The multiple values of the set $\{|W| = \Delta, T_c, j_0\}$ obtained via GBCSEs

Given in **Table 1** are also the values of the set  $\{|W| = \Delta, T_c, j_0\}$  and the constituents of  $j_0$  corresponding to each of the seven choices of  $\lambda$ s mentioned above and the values of  $\mu_s$  given in Eq. (27). Among these, the values of  $|W|$  and  $T_c$  are obtained via Eqs. (14) and (15), respectively. With  $E_F (= \mu_0)$  fixed as in Eq. (27) and the values of  $\gamma$  and  $v_g$  as noted in the legend for **Table 1**,  $s$  and  $n_s$  are calculated via Eqs. (17) and (18), respectively. The values of  $v_0$  and  $j_0$  in each row of **Table 1** are obtained via Eqs. (20) and (21), respectively, with the input of  $\theta = 237$  K, the value of  $\gamma$  noted in it, and the common values of  $\gamma$ ,  $v_g$ , and  $E_F$ .

Excepting  $|W| = 18$  meV in the sixth row, and  $|W| = 38$  meV and  $T_c = 95$  K in the last row of **Table 1**, which were employed as inputs to obtain the three  $\lambda$ s, the values of all the other parameters in the Table are predictions following from our approach. Among these,  $T_c = 62.4$  K, corresponding to  $|W| = 18$  meV in the sixth row, is in excellent agreement with the experimental value, whereas the values of the subset  $\{T_c \text{ (K)}, |W| \text{ (meV)}\} = \{76.8, 26.3\}$  in the fourth row are in reasonable agreement with the experimental values of  $\{86, 28\}$  [see Eq. (23)]. As concerns  $j_0$ , we recall that the experimental value of  $3.2 \times 10^7$  A cm<sup>-2</sup> noted for it in Eq. (24) corresponds to  $T = 4.2$  K and  $H = 12$  Tesla. Since our value of  $j_0 = 7.3 \times 10^7$  A cm<sup>-2</sup> (in the last row of the Table) corresponds to  $T = H = 0$ , it too may be regarded as in reasonably good agreement with the experimental value. Since our approach also provides values of the constituent parameters of  $j_0$ , such as  $n_s$  and  $v_0$ , there is a need to monitor these parameters via experiment for its further validation.

We have so far been concerned with the values of  $\{T_c, \Delta\}$  as noted in Eq. (23). The significance of the additional values of  $T_c$  that GBCSEs have led to, as seen from **Table 1**, is as follows: these are the temperatures at which CPs bound via one- or more-phonon exchange mechanism breakup. Any such  $T_c$  corresponds to vanishing of the associated gap noted in the same row. One would thus expect to see, via appropriately sensitized experimental setups, some of these  $T_c$ s in the resistance vs. temperature plot of the SC. We believe that this expectation is met via the experimental results reported in [24] (reproduced in [25]) where, in a plot of resistance vs. temperature for the Bi-Sr-Ca-Cu-O system obtained via a setup sensitized to determine  $T_c$ s  $\geq 75$  K, there occur discontinuities at 75, 80, 85, 108, and 114 K. While these discontinuities are generally attributed to the presence of more than one phase in the SC, they may well alternatively/additionally be due to the breakdown of one or the other mechanism responsible for pairing.

#### 4.6 Are the results given in Table 1 stable?

To address the above question, which is as relevant in the present context as it is for the numerical solution of any problem, we repeated the entire exercise carried out above by taking the  $\Delta$ - and the  $T_c$ -values of the SC as

$$\Delta_2 = 17.5 \text{ meV}, \Delta_3 = 37.5 \text{ meV}, T_{c3} = 94.5 \text{ K}, \quad (28)$$

which deviate slightly from those considered earlier and noted in Eq. (25). A brief account of the results following from Eq. (28) is as follows:

- i. In order to satisfy the Bogoliubov constraint, we found that we needed

$$\mu_0 = 2.4 k \theta = 49.02 \text{ meV } (\theta = 237\text{K}) \text{ and } \mu_1 = 0.1 \mu_0,$$

i. which led to

$$\{\lambda_{Ca}, \lambda_{Sr}, \lambda_{Bi}\} = \{0.3628, 0.4338, 0.4918\},$$

i. and to values of  $y$  and  $j_0$  in the 1-, 2-, and 3-PEM scenarios as

$$\begin{aligned} \lambda_2 = \lambda_3 = 0 \text{ (1PEM)}, y = 6.353, j_0 = 1.58 \times 10^7 \text{ A/cm}^2 \\ \lambda_1 = 0 \text{ (2PEM)}, y = 1.39, j_0 = 7.21 \times 10^7 \text{ A/cm}^2 \\ \lambda_1 \neq \lambda_2 \neq \lambda_3 \neq 0 \text{ (3PEM)}, y = 1.214, j_0 = 8.24 \times 10^7 \text{ A/cm}^2. \end{aligned}$$

Since the sets of values given in Eqs. (25) and (28) lead to values of  $\Delta_s$ ,  $T_c$ , and  $j_0$  in the same ball park, it is seen that our results are stable with respect to small variations in the input variables.

## 5. Some other applications of GBCSEs

### 5.1 $\text{La}_2\text{CuO}_4$

$\text{La}_2\text{CuO}_4$  is unique not only because it heralded the era of high- $T_c$  superconductivity but also because explanation of its  $T_c \simeq 38$  K via GBCSEs requires invoking 2PEM, whereas it has only kind of ions (La) that can cause pairing. This paradoxical situation is resolved by appealing to the structure of the unit cell of the SC and employing Eqs. (4) and (5) to determine  $\theta_{\text{La}}$ . Since the unit cell comprises layers of LaO and OLa, if La is considered as the upper bob of the double pendulum in one of these, then it must be the lower bob in the other. Eqs. (4) and (5) therefore lead to two values of  $\theta_{\text{La}}$ . We thus have 2PEM in operation due to  $\{\lambda, \theta_{\text{La}1}\}$  and  $\{\lambda, \theta_{\text{La}2}\}$ . Following this approach [10], we were able to account for all the values of  $(2\Delta_0/K_B T_c)$ , i.e., 4.3, 7.1, and 9.3, which were reported by Bednorz and Müller in their Nobel Lecture in 1987.

### 5.2 Heavy fermion SCs (HFSCs)

Superconductivity in HFSCs—so-named because a conduction electron in them behaves as if it has an effective mass up to three orders of magnitude greater than its free mass—was discovered by Steglich et al. [26]. Even though the highest  $T_c$  reported so far for this family of compounds is only 2.3 K (for  $\text{CeCoIn}_5$ ), these SCs have been the subject of avid study by theoreticians because of their following unusual properties:

$$E_F < k\theta, kT_c < E_F, T_c/T_F \approx T_F/\theta \approx 0.05, \quad (29)$$

where  $T_F$  is the Fermi temperature. Besides the properties noted above, HFSCs are characterized by (a) large heat capacities of conduction electrons, much larger than those found for elemental SCs and about as large as those associated with fixed magnetic momenta, and (b) anisotropy of their gap structures. These features caused the term *exotic* or *unconventional* to be coined for them and led to the revival of an old idea that superconductivity may also arise due to the exchange of magnons, rather than just phonons. As a follow-up of this idea, it was shown in three well-known papers [27–29] that several experimental features of HFSCs can be explained if one assumes that magnetic fluctuations are the cause of d-wave

pairing in them. By and large, this seems to be the currently popular view about these SCs.

One of the reasons for regarding HFSCs as outside the purview of BCS theory is the conflict between inequality (8), which is a tenet of the theory, and inequalities (29) which the HFSCs are found to satisfy. Since  $\mu$ -incorporated GBCSEs are not constrained by inequality (8), we employed them for a detailed study of CeCoIn<sub>5</sub>, which is a prominent member of the HFSC family. Salient features of this study are as follows. (i) The pairing mechanism was assumed to be 1PEM because we are dealing with a low value of  $T_c$ . (ii) Since 1PEM can be due to either Co or Ce ions, we considered both of these possibilities. (iii) Using Eqs. (4) and (5) and  $\theta$  (CeCoIn<sub>5</sub>) = 161 K, we found  $\theta_{Ce} = 73$  (276) K, corresponding to Ce as the lower (upper) bob in the double pendulum in the layer containing CeIn<sub>3</sub>, and  $\theta_{Co} = 98.7$ , (294) K (in the layer containing CoIn<sub>3</sub>). (iv) Upon solving the  $\mu$ -incorporated GBCSE for  $\Delta$ , and different values of  $\mu$  in an appropriate range determined via a consideration of inequalities (29), we were led to a multitude of  $\Delta$  values in the range  $(2.76\text{--}3.49) \times 10^{-4}$  eV corresponding to the single value of  $T_c = 2.3$  K. For the SC under consideration, this is in qualitative accord with the experimental finding via the Bogoliubov quasiparticle interference (QPI) technique [the highest  $\Delta$  value thus found is  $(5.5 \pm 0.05) \times 10^{-4}$  eV, whereas our corresponding value based on the mean-field approximation is  $3.49 \times 10^{-4}$  eV]. (v) Some other results

$\left[ n_s = (1/3\pi^2)(2m\mu_1/\hbar^2)^{3/2} \right]$  are as follows:

$$7.84 \times 10^{21} (\mu_1 = 23.81 \text{ meV}, s = 60.4) \geq n_s (\text{cm}^{-3}) \geq 1.07 \times 10^{20} (\mu_1 = 0.324 \text{ meV}, s = 253)$$

$$2.59 \times 10^{22} (\mu_1 = 25.34 \text{ meV}, s = 126) \geq n_s (\text{cm}^{-3}) \geq 3.31 \times 10^{20} (\mu_1 = 0.324 \text{ meV}, s = 539),$$

where the upper row corresponds to pairing via the Ce ions and the lower row to pairing via the Co ions.

It follows from even the brief account given above that the framework of  $\mu$ -incorporated GBCSEs provides a viable explanation of the empirical features of CeCoIn<sub>5</sub> as an alternative to the “popular view” about them; for a more detailed treatment of the SC, we refer the reader to [30].

### 5.3 Fe-based SCs

The salient superconducting properties of Ba<sub>0.6</sub>K<sub>0.4</sub>Fe<sub>2</sub>As<sub>2</sub>, which are generic of the Fe-based SCs (also called iron-pnictide SCs), are as follows (for sources of these properties, see [31]): (i) Superconductivity in this SC is due to the  $s^{\pm}$ -wave state, which signifies that a gap below the Fermi surface and the one corresponding to it above the Fermi surface,  $\Delta_h$  and  $\Delta_e$ , respectively, has opposite signs. (ii) In general,  $\Delta_h \neq \Delta_e$ . (iii)  $T_c = 37$  K. (iv) The highest  $T_c$  reported for this class of SCs > 50 K. (v) Prominent  $\Delta$ -values: 6, 12 meV. (vi) Near-zero values of  $\Delta$ :  $\Delta$  for the SC can fall to zero along lines of its Fermi surface. (vii) Some other reported values of  $\Delta$  (meV): 2.5, 9.0; 3.3, 7.6; 3.6, 8.5, 9.2; 4, 7, 12, 9.5. (viii)  $j_0$ : exceeds  $0.1 \times 10^6 \text{ Acm}^{-2}$  at  $T = 4.2$  K and  $H = 0$ ;  $1.1 \times 10^7 \text{ Acm}^{-2}$  at  $T = 2$  K and  $H = 0$ . (ix) A characteristic ratio for the SC:  $E_F/kT_c = 4.4$ . (x) One of the  $s = m^*/m_e$  values: 9.0 (based on ARPES and a four-band model). (xi) Coherence length  $\xi = 9\text{--}14 \text{ \AA}$ . (xii) The  $T_c$  of the SC plotted against a tuning variable has a dome-like structure.

By adopting the framework of GBCSEs as outlined above, it has been shown in [31] that one can quantitatively explain *all* the above features of Ba<sub>0.6</sub>K<sub>0.4</sub>Fe<sub>2</sub>As<sub>2</sub>—without invoking a new superconducting state for the SC. This is an important remark because, on the basis of the multiband approach, it has been suggested in a recent review article [32] that superconductivity in Fe-based SCs is manifestation of



a *new* state. One of the reasons for this could well be the fact that the BCS equation for  $\Delta$  is quadratic in  $\Delta$  and is therefore unaffected when  $\Delta \rightarrow -\Delta$ . On the other hand, GBCSE for  $W_1$  is linear in this variable and has been derived by assuming that  $W_1$  undergoes a change in signature upon crossing the Fermi surface. This is also a feature of GBCSEs for  $W_2$ , etc. Since  $s^\pm$ -wave is an inbuilt feature of GBCSEs, one does not have to invent a new state for any SC, as has been suggested in [32].

#### 5.4 Isotope-like effect for composite SCs

The following relation between  $T_c$  and the average mass of ions  $M$  in an elemental SC is well-known as the isotope effect:

$$T_c \propto M^{-\alpha}. \quad (30)$$

While in the BCS theory  $\alpha = 0.5$ , values significantly different from it have also been found for some elements such as Mo, Os, and Ru, for which  $\alpha = 0.33, 0.2$ , and  $0$ , respectively. Therefore, while Eq. (30) does not have the status of a *law*, it nonetheless helped in the formulation of BCS theory because it sheds light on the role of the ion lattice in the scenario of 1PEM, which has been shown to be the operative mechanism for elemental SCs.

We now draw attention to the fact that when Bi and Sr. in  $\text{Bi}_2\text{Sr}_2\text{CaCu}_2\text{O}_8$  are replaced by Tl and Ba, respectively, the  $T_c$  of the SC increases from 95 to 110 K. Consequent upon these substitutions, the only property that can be unequivocally determined is the mass of the SC. Because the operative mechanism for pairing in composite SCs is not 1PEM, it becomes interesting to ask if Eq. (30) can be generalized to address the scenarios of 2PEM and 3PEM. A generalization of Eq. (30) that suggests itself naturally for the 2PEM scenario is

$$T_c = p(M_1M_2)^{-\alpha}, \quad (31)$$

where  $p$  is the constant of proportionality and  $M_1$  and  $M_2$  are the masses of ion species that cause pairing. Assuming that the value of  $T_c = 95$  K for  $\text{Bi}_2\text{Sr}_2\text{CaCu}_2\text{O}_8$  is due to 2PEM as in [25], an explanation for the increase in the  $T_c$  of  $\text{Bi}_2\text{Sr}_2\text{CaCu}_2\text{O}_8$  when  $\text{Tl}_2\text{Ba}_2\text{CaCu}_2\text{O}_8$  is obtained from it via substitutions was given in [33]. Noting that Bi and Tl belong to the same period and Sr. and Ba to the same group of the periodic table, several suggestions were made in [33] to further increase the  $T_c$  of the Bi-based SC. An example, following from our study, it was shown that  $T_c$  ( $\text{Bi}_2\text{Mg}_2\text{CaCu}_2\text{O}_8$ ) should be 171 K.

## 6. Discussion

The  $T_c$ s and  $\Delta$ s of most of the hetero-structured, multi-gapped SCs which were studied above via the GBCSE-based approach have also been studied via the more-widely followed multiband approach (MBA) which originated with the work of Suhl et al. [34]. Because the former approach sheds light on additional features of these SCs, such as  $j_0$ ,  $s$ ,  $n_s$ , etc., as also because of its distinctly different conceptual basis, it complements the latter approach. Since the conceptual bases of both the approaches have been dealt with in detail in a recent paper [35], we confine ourselves here to the following remarks:

- i. Employing the concept of a superpropagator, the GBCSE-based approach invariably invokes a  $\lambda$  for each of the ion species in an SC that may cause

pairing. One then has the same  $\lambda$ s in the equations for any  $\Delta$  and the corresponding  $T_c$  of the SC—as is the case for elemental SCs. Multiple gaps arise in this approach because different combinations of  $\lambda$ s operate on different parts of the Fermi surface due to its undulations. For a discussion of the moot question concerning the assumption of *locally* spherical values characterizing the Fermi surface of a composite SC, see [33].

On the other hand, the number of bands employed in MBA for the same SC differs from author to author. In this approach, in the two-band models, multiple gaps arise because the Hamiltonian is now postulated to have a term for pairing in each of the bands and another term corresponding to crossband pairing. For the  $T_c$  of the SC, one often employs the Migdal-Eliashberg-McMillan approach [36] which, even though based on 1PEM, allows  $\lambda$  to be greater than unity because it is based on an integral equation and the expansion parameter of which is not  $\lambda$  but  $m_e/M$ , where  $M$  is the mass of an ion species.

- ii. Because of the feature of the GBCSE-based approach discussed above, with the input of the values of any two gaps of an SC and a value of  $T_c$ , it goes on to shed light on several other values of these parameters. This is not so for MBA.

## 7. Conclusions

- i. Besides the SCs dealt with above, the GBCSE-based approach has been applied for the study of several elemental SCs,  $MgB_2$ , YBCO and Tl-2212 [10, 19, 20],  $SrTiO_3$  [10], and NbN [21]. It is hence seen that a striking feature of this approach is its versatility: it is applicable to a wide variety of SCs that includes the so-called exotic or unconventional SCs such as the HFSCs and the Fe-based SCs, without invoking a new superconducting state for the latter.
- ii. We believe to have shown that in explaining the empirical features of high- $T_c$  SCs, the GBCSE-based approach goes farther than MBA or, so far as we are aware, any other approach, e.g., [37].
- iii. The fact that  $T_c(Bi_2Sr_2Ca_2Cu_3O_{10}) > T_c(Bi_2Sr_2CaCu_2O_8) > T_c(YBa_2Cu_3O_7) > T_c(MgB_2)$ , etc., obviously suggests that the greater the complexity of structure of the SC, the greater is its  $T_c$  owing to the increase in the number of channels that may cause formation of CPs. While this is a situation that the GBCSE-based approach can easily deal with, in practice, going beyond  $Bi_2Sr_2Ca_2Cu_3O_{10}$ , for example, is most likely to lead to an unstable and hence unrealizable SC. This is a problem that we believe belongs to the realm of chemical engineering.
- iv. It was noted above that 14 different values of  $j_0$  have been reported for Bi-2212. For none of these values were reported the values of the other superconducting parameters of the SC. On the basis of [19, 20], we believe that, in order to help theory to suggest means to increase the  $T_c$  of an SC, the report of any of its properties, for example,  $j_0$ , should be accompanied by, in so far as it is experimentally feasible, a list of all its other superconducting properties, viz.,  $\theta$ ,  $T_c$ ,  $\Delta$ s,  $m^*$ ,  $v_0$ ,  $n_s$ ,  $\gamma$ , and  $v_g$ .
- v. The  $E_F$ -incorporated GBCSEs in this communication correspond to the  $T_c$  of a composite SC and its  $\Delta$ -values at  $T = H = 0$ . These equations can be further

generalized to deal with the situation when the SC is in heat bath in an external magnetic field, i.e., when  $T \neq H \neq 0$ , a procedure for which has been given in [38]. The import of this remark is that not only will such an undertaking enable theory to address the  $j_0$  values of an SC which are generally reported for such values of T and H but also that it may shed new light on the Volovik effect for the Fe-based SCs, as discussed in, e.g., [32].

### **Conflict of interest**

The authors declare that there is no conflict of interest with regard to this submission.

### **Author details**

Gulshan Prakash Malik<sup>1\*†</sup> and Vijaya Shankar Varma<sup>2‡</sup>

1 Sushant Lok 1, Gurgaon, Haryana, India


2 Mall Apartments, Mall Road, Delhi, India

\*Address all correspondence to: [gulshanpmalik@yahoo.com](mailto:gulshanpmalik@yahoo.com)

†Formerly: Theory Group, School of Environmental Sciences, Jawaharlal Nehru University, New Delhi, India

‡Formerly: Department of Physics and Astrophysics, University of Delhi, Delhi, India

### **IntechOpen**

© 2019 The Author(s). Licensee IntechOpen. This chapter is distributed under the terms of the Creative Commons Attribution License (<http://creativecommons.org/licenses/by/3.0>), which permits unrestricted use, distribution, and reproduction in any medium, provided the original work is properly cited. 

## References

- [1] Onnes Kamerlingh H. Further experiments with liquid helium. G. On the electrical resistance of pure metals, etc. VI. On the sudden change in the rate at which the resistance of mercury disappears. Communications from the Laboratory of Physics at the University of Leiden. 1911;**124c**:267-271
- [2] Bardeen J, Cooper LN, Schrieffer JR. Theory of superconductivity. Physics Review. 1957;**108**:1175-1204. DOI: 10.1103/PhysRev.108.1175
- [3] Salpeter EE, Bethe H. A relativistic equation for bound-state problems. Physics Review. 1951;**84**:1232-1242. DOI: 10.1103/PhysRev.84.1232
- [4] Matsubara T. A new approach to quantum-statistical mechanics. Progress of Theoretical Physics. 1955;**14**:351-378. DOI: 10.1143/PTP.14.351
- [5] Okubo S. Note on the second kind interaction. Progress of Theoretical Physics. 1954;**11**:80-94. DOI: 10.1143/PTP.11.80
- [6] Dolan L, Jackiw R. Symmetry behavior at finite temperature. Physics Review. 1974;**D9**:3320-3341. DOI: 10.1103/PhysRevD.9.3320
- [7] Biswas SN, Malik GP, Sudarshan ECG. Superpropagator for a nonpolynomial field. Physics Review. 1973;**D7**:2884-2886. DOI: 10.1103/PhysRevD.7.2884
- [8] Seitz F. Modern Theory of Solids. NY: McGraw Hill; 1940. 698 p. ISBN-10: 9780070560307; ISBN-13: 978-0070560307; ASIN: 0070560307
- [9] Blatt JM. Theory of Superconductivity. NY: Academic Press; 1964. 486 p. QC612.S8B57
- [10] Malik GP. Superconductivity – A New Approach Based on the Bethe-Salpeter Equation in the Mean-Field Approximation. Volume 21 in the series on condensed matter physics. Singapore: World Scientific; 2016. 223 p. ISBN 9814733075 (hard cover)
- [11] Salpeter EE. Mass corrections to the fine structure of hydrogen-like atoms. Physics Review. 1952;**87**:328-343. DOI: 10.1103/PhysRev.87.328
- [12] Lee DH. Iron-based superconductors: Nodal rings. Nature Physics. 2012;**8**:364-365. DOI: 10.1038/nphys2301
- [13] Zhang Y et al. Nodal superconducting-gap structure in ferropnictide superconductor BaFe<sub>2</sub>(As<sub>0.7</sub>P<sub>0.3</sub>)<sub>2</sub>. Nature Physics. 2012;**8**:371-375. DOI: 10.1038/nphys2248
- [14] Allan MP et al. Anisotropic energy gaps of iron-based superconductivity from intra-band Quasiparticle interference in LiFeAs. Science. 2012;**336**:231-236. DOI: 10.1126/science
- [15] Alexandrov AS. Nonadiabatic polaronic superconductivity in MgB<sub>2</sub> and cuprates. Physica C: Superconductivity. 2001;**363**:231-236. DOI: 10.1016/S0921-4534(01)01095-4
- [16] Jarlborg T, Bianconi A. Fermi surface reconstruction of superoxygenated La<sub>2</sub>CuO<sub>4</sub> superconductors with ordered oxygen interstitials. Physical Review B. 2013;**87**:054514-054516. DOI: 10.1103/PhysRevB.87.054514
- [17] van der Marel D, van Mechelen JLM, Mazin II. Common Fermi-liquid origin of T<sup>2</sup> resistivity and superconductivity in n-type SrTiO<sub>3</sub>. Physical Review B. 2011;**84**:205111-205111. DOI: 10.1103/PhysRevB.84.205111
- [18] Eagles DM. Possible pairing without superconductivity at low carrier

concentrations in bulk and thin-film superconducting semiconductors. *Physics Review*. 1969;**186**:456-463. DOI: 10.1103/PhysRev.186.456

[19] Malik GP. On the role of fermi energy in determining properties of superconductors: A detailed study of two elemental superconductors (Sn and Pb), a non-cuprate ( $\text{MgB}_2$ ) and three cuprates (YBCO, Bi-2212 and Tl-2212). *Journal of Superconductivity and Novel Magnetism*. 2016;**29**:2755-2764. DOI: 10.1007/s10948-016-3637-5

[20] Malik GP. Correction to: On the role of fermi energy in determining properties of superconductors: A detailed study of two elemental superconductors (Sn and Pb), a non-cuprate ( $\text{MgB}_2$ ) and three cuprates (YBCO, Bi-2212 and Tl-2212). *Journal of Superconductivity and Novel Magnetism*. 2018;**31**:941. DOI: 10.1007/s10948-017-4520-8

[21] Malik GP. A detailed study of the role of Fermi energy in determining properties of superconducting NbN. *Journal of Modern Physics*. 2017;**8**: 99-109. DOI: 10.4236/jmp.2017.81009

[22] Poole CP. *Handbook of Superconductivity*. San Diego: Academic Press; 2000. 692 p. ISBN: 0-12-561460-8, Library of Congress Card No.: 99-60091

[23] Kametani F, et al. Comparison of growth texture in round Bi2212 and flat Bi2223 wires and its relation to high critical current density development. *Scientific Reports*. 2015;**5**. Article Number 8285. DOI: 10.1038/srep08285

[24] Hiroshi M, Kazumasa T, editors. *Bismuth-Based High-Temperature Superconductors*. NY: Marcel-Dekker; 1996. 626 p. ISBN: 0-8247-9690-X (alk. paper)

[25] Malik GP, Malik U. A study of thallium- and bismuth-based high-

temperature superconductors in the framework of the generalized BCS equations. *Journal of Superconductivity and Novel Magnetism*. 2011;**24**:255-260. DOI: 10.1007/s10948-010-1009-0

[26] Steglich F et al. Superconductivity in the presence of strong Pauli Paramagnetism:  $\text{CeCu}_2\text{Si}_2$ . *Physical Review Letters*. 1976;**43**:1892-1896. DOI: 10.1103/PhysRevLett.43.1892

[27] Miyaki K, Rink SS, Varma CM. Spin-fluctuation-mediated even-parity pairing in heavy-fermion superconductors. *Physical Review B*. 1986;**34**:6554-6556. DOI: 10.1103/PhysRevB.34.6554

[28] Monod MT, Bourbonnias C, Emery V. Possible superconductivity in nearly antiferromagnetic itinerant fermion systems. *Physical Review B*. 1986;**34**: 7716-7720. DOI: 10.1103/PhysRevB.34.7716

[29] Scalapino DJ, Loh E, Hirsch JE. D-wave pairing near a spin-density-wave instability. *Physical Review B*. 1986;**34**:8190-8192. DOI: 10.1103/PhysRevB.34.8190

[30] Malik GP. A study of heavy-fermion superconductors via BCS equations incorporating chemical potential. *Journal of Modern Physics*. 2015;**6**: 1233-1242. DOI: 10.4236/jmp.2015.69128

[31] Malik GP. On the  $s^\pm$ -wave superconductivity in the iron-based superconductors: A perspective based on a detailed study of  $\text{Ba}_{0.6}\text{K}_{0.4}\text{Fe}_2\text{As}_2$  via the generalized Bardeen-Cooper-Schrieffer equations incorporating Fermi energy. *Open Journal of Composite Materials*. 2017;**7**:130-145. DOI: 10.4236/ojcm.2017.73008

[32] Bang Y, Stewart GR. Superconducting properties of the  $s^\pm$ -wave state: Fe-based superconductors. *Journal of Physics. Condensed Matter*.

2017;29:123003-123046. DOI: 10.1088/1361-648X/aa564b

[33] Malik GP. On the isotope-like effect for high- $T_c$  superconductors in the scenario of 2-phonon exchange mechanism for pairing. *World Journal of Condensed Matter Physics*. 2018;8:109-114. DOI: 10.4236/wjcmp.2018.83007

[34] Suhl H, Matthias BT, Walker LR. Bardeen-Cooper-Schrieffer theory in the case of overlapping bands. *Physical Review Letters*. 1959;3:552-554. DOI: 10.1103/PhysRevLett.3.552

[35] Malik GP. An overview of the multi-band and the generalized BCS equations-based approaches to Deal with hetero-structured superconductors. *Open Journal of Microphysics*. 2018;8:7-13. DOI: 10.4236/ojm.2018.82002

[36] McMillan WL. Transition Temperature of Strong-Coupled Superconductors. 1968;167:331-344. DOI: 10.1103/PhysRev.167.331

[37] Freeman J, Sandro Massida JY. Local density theory of high  $T_c$  superconductors:  $Ba_2Sr_2CaCu_2O_8$ . *Physica C: Superconductivity*. 1988;153-155:1225-1226. DOI: 10.1016/0921-4534(88)90253-5

[38] Malik GP. On Landau quantization of Cooper pairs in a heat bath. *Physica B: Condensed Matter*. 2010;405:3475-3481. DOI: 10.1016/j.physb.2010.05.026